## Page f L of $_1$



## Eshamac PM

## Polymer-modified repair asphalt

Factory descriptor Eshamac PM

Grading 0/3 | 0/5 | 0/8 | 0/11

Application For quick and long-lasting repairs to horizontal asphalt layers, in particular for damage

to the top coat and cracking in pavement on roads, sidewalks, or even parking lots.

Properties Eshamac PM is a cold, ready-mixed repair asphalt.

We manufacture this product using a select, graded grain-size distribution and a specially developed polymer-modified bitumen emulsion. When properly applied, it

can repair the damaged areas with a long-lasting effect.

Handling It is important to choose the right grading based on the depth of the damage:

Eshamac PM 0/3

to up 1 cm paving thickness – approx. 10–25 kg/m² of material necessary

Eshamac PM 0/5

to up 2 cm paving thickness – approx. 20–40 kg/m² of material necessary

Eshamac PM 0/8

to up 4 cm paving thickness – approx. 35–80 kg/m² of material necessary

Eshamac PM 0/11

to up 6 cm paving thickness – approx. 75–115 kg/m<sup>2</sup> of material necessary

After choosing the appropriate grading, and without applying joint tapes, the material is applied to a load-bearing surface, which has been sufficiently cleaned. Once the blend has been distributed throughout the damaged area, it must be compacted using a hand tamper, vibrating compactor, or light roller, depending on the surface area.

Eshamac PM is ready for loading immediately after compacting.

Packaging 25 kg plastic bucket | Disposable packaging

bulk

Storage plastic bucket | Unopened buckets can be stored for up to twelve months.

bulk | Immediate use. Bulk products must be covered by a tarpaulin when in storage.

Information Please consult our website for further information at any time.

All information provided here is correct to the best of our knowledge in terms of development and application. It should not be understood as any guarantee of the suitability for particular applications, as it is only meant to provide information on our products. We reserve the right to make changes to this product specification sheet at any time.